

# DUMACRYL 60 260 X

## Thermosetting Acrylic Polyol

### Primary Usages

2K systems,  
Metal and wood coating,  
Industrial paints and varnishes,  
Refinish car paints,  
Marine paints and varnishes,  
Curing with HDI or TDI polyisocyanates

### Packaging

Net 200 Kg in Steel Drum  
Net 1.000 Kg in IBC  
Bulk

### Product Features

High gloss,  
Excellent weathering properties,  
Excellent chemical resistance,  
Excellent hardness

### Technical Specifications

| Test                                | Range   |
|-------------------------------------|---------|
| Solid Content (%)                   | 58 - 62 |
| Viscosity (25°C, GHT)               | Y - Z2  |
| Color (Gardner, 50%)                | Max. 1  |
| Acid Value (mg KOH/g)               | Max. 13 |
| OH Value (on Solid)                 | 2,6     |
| Density (gr/cm <sup>3</sup> , 20°C) | 0,99    |

### Dilutability

|               |           |
|---------------|-----------|
| White Spirit  | Insoluble |
| Toluene       | Complete  |
| Xylene        | Complete  |
| Butyl Acetate | Complete  |

### Composition

|                     |        |
|---------------------|--------|
| Solvent Composition | Xylene |
|---------------------|--------|

### Compatibility

|                          |          |
|--------------------------|----------|
| Aliphatic polyisocyanate | Complete |
| Aromatic polyisocyanate  | Complete |

### Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

### Material Safety

A Material Safety Data Sheet for this product is available on request.