

DUMADRY Zr Octoate

Zirconium Octoate

Product Description

Zirconium Octoate siccatives particularly recommended in order to prevent ecologic disadvantages of Lead driers. It is recommended usage amount is between 0,1% - 0,3% based on solid content. Zirconium Octoate is generally used with Cobalt siccatives in order to obtain a hard and durable film layer. Suitable to be used instead of Lead driers. Recommended amount is 75% of Lead Octoate.

Properties	Zr Oct 6	Zr Oct 10	Zr Oct 12	Zr Oct 18	Zr Oct 24
Metal Content (%)	6 ± 0.2	10 ± 0.2	12 ± 0.2	18 ± 0.2	24 ± 0.2
Appearance	Liquid	Liquid	Liquid	Liquid	Liquid
Color	Colorless	Colorless	Colorless	Colorless	Colorless
Viscosity (sec, 20°C)	0,5 - 1,5	1 - 2	1,5 - 2,5	5,5 - 6,5	55 - 60
Solid Content (%)	15 ± 2	25 ± 2	30 ± 2	45 ± 2	65 ± 2
Solvent Type	White Spirit	White Spirit	White Spirit	White Spirit	White Spirit
Density (gr/cm ³ , 20°C)	0,83 ± 0,01	0,89 ± 0,01	0,92 ± 0,01	1,03 ± 0,01	1,15 ± 0,01
Packaging (Steel Drum)	180 Kg	180 Kg	180 Kg	200 Kg	200 Kg

Storage Conditions

Protect from direct sunlight and frost. In its original packaging (plastic containers, barrels, drums, etc.), between 5 - 30°C, can be stored for 1 year.

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.