



DUMAN

Technical Data Sheet

DUMAKYD 65 50 X

Medium Oil Alkyd Resin

Primary Usages

Air drying interior and exterior industrial finishes,
Anticorrosive paints,
Metal and wood surface coatings,
Industrial paints and varnishes

Packaging

Net 200 Kg in Steel Drum
Net 1.000 Kg in IBC
Bulk

Product Features

High chemical and weathering resistance,
Good gloss and gloss retention,
Very good yellowing resistance

Technical Specifications

Test

Solid Content (%)
Viscosity (25°C, GHT)
Color (Gardner, 50%)
Acid Value (mg KOH/g)
Density (gr/cm³)

Range

64 - 66
Z2 - Z3 (%65)
Max. 5
Max. 11
1,08

Dilutability

Xylene	Complete
White Spirit	Limited
Toluene	Complete
n-Butanol	Insoluble
Methyl Ethyl Ketone	Complete

Composition

Oil Content	~ 50%
Type of Oil	Soyabean / Sunflower Oil
Solvent Composition	Xylene

Compatibility

Hydroxyl acrylic resins	Limited
Long oil alkyds	Limited
Short oil alkyds	Complete
Cellulose nitrate	Complete
Aliphatic polyisocyanate	Complete
Aromatic polyisocyanate	Complete
Amino resins	Complete

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

Recommended Dryer Combinations

DUMADRY Co Octoate	0,04-0,06%
DUMADRY Zr Octoate	0,2-0,4%
DUMADRY Ca Octoate	0,1-0,3%

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.