



DUMAN

Technical Data Sheet

DUMAKYD 70 45 W

Medium Oil Alkyd Resin

Primary Usages

Air drying interior and exterior industrial finishes,
Metal anticorrosive primers,
Undercoats,
Air drying finishes and wood varnishes

Packaging

Net 195 Kg in Steel Drum
Net 950 Kg in IBC
Bulk

Product Features

Excellent drying and durability,
High gloss and gloss retention,
Resistance is mild in humid conditions,
Good mechanical properties

Technical Specifications

Test

Solid Content (%)
Viscosity (25°C, GHT)
Color (Gardner, 50%)
Acid Value (mg KOH/g)
Density (gr/cm³)

Range

69 - 71
X - Z2 (%55)
Max. 7
Max. 12
1,06

Dilutability

Xylene	Complete
White Spirit	Complete
Toluene	Complete
n-Butanol	Limited

Composition

Oil Content	~ 45%
Type of Oil	Soyabean/Sunflower Fatty Acid
Solvent Composition	White Spirit

Compatibility

Hydroxyl acrylic resins	Limited
Long oil alkyds	Limited
Short oil alkyds	Complete
Cellulose nitrate	Complete
Aliphatic polyisocyanate	Complete
Aromatic polyisocyanate	Complete
Amino resins	Complete

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

Recommended Dryer Combinations

DUMADRY Co Octoate	0,04-0,06%
DUMADRY Zr Octoate	0,2-0,4%
DUMADRY Ca Octoate	0,1-0,3%

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.