



Technical Data Sheet

DUMAMIDE 70 1115 X

Polyamide Epoxy Curing Agent

Primary Usages

2K Systems,
High solids systems,
Anticorrosive industrial paints,
Industrial maintenance,
Enamel paints

Packaging

Net 180 Kg in Steel Drum

Product Features

Excellent resistance properties and adhesion,
Superior corrosion resistance,
Very good gloss retention,
Outstanding mechanical properties

Technical Specifications

Test	Range
Solid Content (%)	69 - 71
Viscosity (25°C, cP)	900 - 1700
Color	Max. 10
Amine Value (mg KOH/gr)	185
Approx. AHEW (gr/mol)	310
Density (20°C)	0,94

Dilutability

Toluene	Complete
Xylene	Complete
Acetone	Complete

Composition

Solvent Composition	Xylene
---------------------	--------

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.