



DUMAN

Technical Data Sheet

DUMAPOL 66 70 BS

Saturated Polyester Resin

Primary Usages

Stoving coating,
Coil coating primer,
Can coating,
Industrial paints and varnishes,
Refinish car paints

Packaging

Net 200 Kg in Steel Drum
Net 1.000 Kg in IBC
Bulk

Product Features

Excellent weathering properties,
Good application properties,
Low molecular weight

Technical Specifications

Test

Solid Content (%)
Viscosity (Brookfield 25°C, cP)
Color (Gardner, %50)
Acid Value (mg KOH/g)
OH Value (on Solid)
Molecular Weight (gr/mol)
Density (gr/cm³, 20°C)

Range

64 - 68
900 - 1500
Max. 2
Max. 6
1,50 - 2,10
4000-6500
1,10

Dilutability

Acetone Complete

Composition

Solvent Composition Butyl Glycol / Solvent Naphta

Compatibility

CAB Complete

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.

Cevizlik Mah. İstanbul Cad. Güven İş Hanı Sitesi, No: 41, İç Kapı No: 100, 34142, Bakırköy/İstanbul

Phone: +90 541 386 2654

www.dumanchem.com