



Technical Data Sheet

DUMAPOX 75 1008 X

Solvent Borne Epoxy Resin

Primary Usages

2K Systems,
Metal coatings,
Marine paints,
Anticorrosive industrial paints,
Industrial Paints and Varnishes

Packaging

Net 220 Kg in Steel Drum

Product Features

Excellent for mechanical strength,
High resistance to chemicals,
Adhesive strength

Technical Specifications

Test

Solid Content (%)
Viscosity (25°C, cP)
Color
EEW (g/eq)

Range

74 - 76
8000 - 13000
Max. 1
450 - 500

Dilutability

Toluene	Complete
Xylene	Complete
Acetone	Complete

Composition

Solvent Composition	Xylene
---------------------	--------

Storage and Shelf Life Condition

The resin should be stored indoors in original, unopened, undamaged container in a dry place at storage temperature between 5-30 °C. Exposure to direct sunlight should be avoided. The shelf life of the resin which under the mentioned storage conditions is 12 months.

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.