

DUMASOL 215

Pure Acrylic Copolymer Emulsion

Product Description

Direct to Metal (DTM) finishes and topcoats with excellent gloss properties.

Technical Specifications

Chemical Structure	:	Pure Acrylic Copolymer
Appearance	:	Milky white
Density (25°C, g/cm ³)	:	1,06
Total Solids (%)	:	44 - 46
Viscosity (cP, 25°C)	:	Max. 500
pH	:	7 - 8
MFFT (°C)	:	+ 31

Primary Usages

Direct to Metal
Gloss Paints
Interior Paints
Exterior Paints

Product Features

Excellent glossy effect with gloss reflection
Excellent corrosion resistance
Excellent chemical and solvent resistance
Excellent adhesion to metal substrates
Excellent interior & exterior durability

Storage Conditions

Protect from direct sunlight and frost. In its original packaging (plastic containers, barrels, drums, etc.), between 5 - 30°C, can be stored for 1 year.

Packaging

Net 180 Kg in Plastic Drum
Net 1050 Kg in IBC
Bulk

Material Safety

A Material Safety Data Sheet for this product is available on request.

The information in this data sheet is to the best of our knowledge correct at the date of printing. They merely serve the purpose of informing our customers and do not relieve them from examining themselves the suitability of the described products for the intended purpose. Since conditions of the application are beyond our control, no liability can be accepted on the basis of this data sheet.